

## OFFICIAL JOURNAL OF THE PATENT OFFICE

निर्गमन सं. 44/2022	शुक्रवार	दिनांकः 04/11/2022
<b>ISSUE NO. 44/2022</b>	FRIDAY	DATE: 04/11/2022

## पेटेंट कार्यालय का एक प्रकाशन PUBLICATION OF THE PATENT OFFICE

The Patent Office Journal No. 44/2022 Dated 04/11/2022

(12) PATENT APPLICATION PUBLICATION

(54) Title of the invention : Low cost Biodegradable plastic production using Nanotechnology

(19) INDIA(22) Date of filing of Application :26/10/2022

		<ul> <li>(71)Name of Applicant :</li> <li>1)Tr. Perala Sudheer Paul Address of Applicant :Research Scholar, Department of Environmental Sciences, AU College of Science &amp; Technology, Andhra</li> </ul>
<ul> <li>(51) International classification</li> <li>(86) International Application No Filing Date</li> <li>(87) International Publication No</li> <li>(61) Patent of Addition to Application Number Filing Date</li> <li>(62) Divisional to Application Number Filing Date</li> </ul>	:B65D0065460000, C08J0009120000, B29C0044340000, C08B0030200000, C08L0003120000 :PCT// :01/01/1900 : NA 'NA :NA :NA :NA	University, Visakhapatnam, Andhra Pradesh, India, Pincode:530003 2)Dr. Pallavi N 3)Dr. Roohi 4)Dr. M. Parthasarathy 5)Dr. Ikechukwu Peter EJIDIKE 6)Mr. Kotta Apparao 7)Dr. Ashish Verma Name of Applicant : NA Address of Applicant : NA (72)Name of Inventor : 1)Tr. Perala Sudheer Paul Address of Applicant :Research Scholar, Department of Environmental Sciences, AU College of Science & Technology, Andhra University, Visakhapatnam, Andhra Pradesh, India, Pincode:530003 2)Dr. Pallavi N Address of Applicant :Assistant Professor, Department of Environmental Sciences, JSS Academy of Higher Education & Research, Mysuru, Karnataka, India, Pincode:570015 3)Dr. Roohi Address of Applicant :Associate Professor, Department of Bio Engineering, Integral University, Lucknow, Uttar Pradesh, India, Pincode: 226026

## (57) Abstract :

A biodegradable packaging material comprising an expanded high amylose starch product having a minimum amylose content of at least 45% by weight, said expanded product has a low density, closed cell structure with excellent resilience and compressibility. Extruding a starch that has an amylose content of at least 45% by weight in the presence of a total moisture content that is 21% or less by weight while the temperature is between 150 and 250 degrees Celsius is one method that can be used to prepare a low density, biodegradable packaging material. This method is provided by another embodiment of the invention.

No. of Pages : 21 No. of Claims : 5